


2.75" K-13 ACOUSTIC/ THERMAL INSULATION ASTM C-423 ON 3" FLUTED METAL DECK



K-13 ACOUSTIC/ THERMAL INSULATION ASTM C-423 ON 3" FLUTED METAL DECK*							
INCHES	125 hZ	250 hZ	500 hZ	1,000 hZ	2,000 hZ	4,000 hZ	NRC
1.5"	0.55	0.92	1.11	1.02	0.95	0.99	1.00
2.75"	0.69	0.98	1.17	1.03	0.97	1.04	1.05

*Some Values Interpolated

DATE:

NOTES:



**INTERNATIONAL
CELLULOSE
CORPORATION**

12315 ROBIN BLVD. HOUSTON, TX 77045
icc@spray-on.com | 800.444.1252
www.spray-on.com